

TECHNICAL DATASHEET


Method Summary:

The refractive index and percent light transmission of the Gel polymer material was measured at various wavelengths.

Refractive Index:

Wavelength	589 nm	633 nm	1321 nm	1554 nm
Refractive Index	1.41	1.42	1.40	1.40

Percent Transmission:



Analysis performed by Gel material supplier.