



## GEL IONIC PROPERTIES

---

### Technical Datasheet

#### METHOD SUMMARY

Ion Chromatography utilizes ion exchange to separate and identify anions and cations

#### TEST STANDARD

Method adapted from EPA Test Method 300.0; EPA-600/4-84-017, ASTM E 180

#### TEST METHOD AND RESULTS

Dionex DX-500 Ion Chromatography

The Gel polymer material utilized in AD, BD, CD, PF, WF and VR products was analyzed by Ion Chromatography. The following are the measured results for the various anions and cations:

Sample	Na <sup>+</sup>	NH <sub>4</sub> <sup>+</sup>	K <sup>+</sup>	Cl <sup>-</sup>	NO <sub>3</sub> <sup>-</sup>	SO <sub>4</sub> <sup>2-</sup>
Gel	0.4050 ppm	0.1660 ppm	Not Detected	2.3720 ppm	2.1203 ppm	0.5536 ppm

\* ppm = parts per million

\* Reportable Detection Limit = 0.20 ppm

#### RESULTS SUMMARY

Ion Chromatography was used to identify the following anions and cations in the Gel material: sodium, ammonium, chloride, nitrate, and sulfate. No potassium was detected.

#### GEL-PAK

31398 Huntwood Avenue, Hayward, CA 94544

**Toll-Free** 888-621-4147 **Phone** 510-576-2220 **Fax** 510-576-2282

**Website** [www.gelpak.com](http://www.gelpak.com)

Division of

**DELPHON**