



GEL MATERIAL PROPERTIES

Technical Datasheet

Typical Properties	Unit	Value
Shelf Life (minimum)	Years	2
Color	-	Clear
Temperature	°C	-40 to 220
Volume Resistivity	ohm-cm	2.0x10 ¹⁵
Elongation at Break	%	140
Coefficient of Thermal Conductivity	W/(m·K)	0.17
Elastic Modulus	KPa	1,000
Tensile Strength	MPa	7.1
Specific Gravity at 23 °C	-	1.05

Note: These values are for reference purposes only and are not intended for use in preparing specifications.

GEL-PAK

31398 Huntwood Avenue, Hayward, CA 94544

Toll-Free 888-621-4147 **Phone** 510-576-2220 **Fax** 510-576-2282

Website www.gelpak.com

Division of

DELPHON