



VERTEC FK79 MATERIAL PROPERTIES

Technical Datasheet

Material Property	Value
Chemistry	Proprietary Thermoplastic Elastomer
Surface Tack	High Tack
Surface Resistance	10 ¹⁵ ohms
Durometer	37 - 45 Shore A
Elongation at Break	500%
Shear Modulus (G')	367 kPa
Operating Temperature	+10 to +35 °C
Shipping/Storage Temperature	0 to +60 °C (see note 2)
Shelf Life	2 Years

NOTES:

1. *These values are for reference purposes only and are not intended for use in preparing specifications.*
2. *Extended temperature ranges are possible, however testing may be needed.*

GEL-PAK

31398 Huntwood Avenue, Hayward, CA 94544

Toll-Free 888-621-4147 **Phone** 510-576-2220 **Fax** 510-576-2282

Website www.gelpak.com

Division of

DELPHON