

VERTEC FK79 MATERIAL PROPERTIES

Technical Datasheet

Material Property	Value
Chemistry	Proprietary Thermoplastic Elastomer
Surface Tack	Medium Tack
Surface Resistance	10 ¹³ ohms
Durometer	36 - 46 Shore A
Elongation at Break	500%
Shear Modulus (G')	440 kPa
Operating Temperature	+10 to +35 °C
Shipping/Storage Temperature	0 to +60 °C (see note 2)
Shelf Life	2 Years

NOTES:

- 1. These values are for reference purposes only and are not intended for use in preparing specifications.*
- 2. Extended temperature ranges are possible, however testing may be needed.*

GEL-PAK

31398 Huntwood Avenue, Hayward, CA 94544

Toll-Free 888-621-4147 **Phone** 510-576-2220 **Fax** 510-576-2282

Website www.gelpak.com

Division of

DELPHON