

VERTEC EH07 MATERIAL PROPERTIES

Technical Datasheet

Material Property	Value
Chemistry	Proprietary Thermoset Polyurethane Elastomer
Surface Tack	High Tack
Surface Resistance	<10 ⁹ ohms
Durometer	60 - 68 Shore OO
Elongation at Break	NA
Shear Modulus (G')	200 kPa
Operating Temperature	+10 to +35 °C
Shipping/Storage Temperature	-10 to +75 °C (see note 2)
Shelf Life	2 Years

NOTES:

1. *These values are for reference purposes only and are not intended for use in preparing specifications.*
2. *Extended temperature ranges are possible, however testing may be needed.*

GEL-PAK

31398 Huntwood Avenue, Hayward, CA 94544

Toll-Free 888-621-4147 **Phone** 510-576-2220 **Fax** 510-576-2282

Website www.gelpak.com

Division of

DELPHON